

品说明书

TECHNICAL DATA SHEET

TYL-6B20/40A-E, TYL-6B20/40B-E

加成型液体硅橡胶

Addition type liquid silicone rubber

简述 BRIEF INTRODUCTION

本产品为双组分包装的加成型液体硅橡胶,适宜采用液体注射成型方法加工成型制品。 The product is a Two-component cure LSR which is suggested to processed by liquid injection molding.

2 主要特征 KEY FEATURES

产品成型效率高, 废边少, 节约能源

Forming efficiency, scrap, energy conservation

良好的综合物理性能,制品透明度高

Good physical properties, high transparency

符合ISO 10993-4、ISO 10993-5、ISO 10993-10、ISO 10993-11

Pass ISO 10993-4, ISO 10993-5, ISO 10993-10, ISO 10993-11

符合USP<88> class VI

Pass USP<88> class VI

符合LFGB认证

Pass LFGB

符合FDA 认证

Pass FDA

符合RoHS认证

Pass RoHS

3 主要用途 **APPLICATIONS**

医用纺织物涂层

Medical textile fabrics coating

医用商标胶

Medical trademark silicone

其他医疗用品及配件

Other medical products and accessories

4 包装 PACKAGE

20 kg/桶,标准塑料直桶,内衬专用塑料袋。

地址 (Address):

No.36, Jingling Road, Qingyuan High-tech Zone, Qingyuan Guangdong China. 传真 (Fax):

电话 (Tel) (+86) 0763-3608674 网址 (Website): www.wynca.com

邮编(Postcode): 511500

(+86) 0763-3608675

Page 1 / 4

中国广东省清远市高新技术产业开发区井岭路36号



20 kg / barrel, standard plastic barrel, with special plastic bag inside.

200 kg/桶,标准金属直桶,内衬专用塑料袋,花格木箱外包装。 200 kg / barrel, the standard metal barrel, with special plastic bag inside.

5 运输、安全及储存注意事项 NOTICE FOR TRANSPORTATION, SAFETY AND STORAGE

产品安全信息不包括产品的具体使用指导。

Product safety information does not include specific instructions for the use of the product.

使用前,请仔细阅读产品的使用说明和产品安全数据表,以及产品包装上的指示说明, 使用若需要详细的安全信息,请向销售办事处索取材料安全数据表。

Please read the product instructions and product safety data sheet carefully, as well as the instructions on the product package before use. If you need detailed safety information, please ask the sales office for the material safety data sheet.

本产品无毒、无害,按非危险品运输;不可倒置,运输中应避免摔跌,避免与尖硬锐物

The non-toxic, harmless, non-dangerous This product is non-toxic and harmless. Transport according to rules of non-dangerous goods. Avoid tumble and collision with hard or sharp objects.

请在室温、通风、避雨防潮、避太阳直照下贮存。

Please store in water and damp-proof place at room temperature, keep ventilation, and avoid the direct sunlight.

保存期:胶料自生产日期起,室温可以存放12个月,6个月内使用为最佳。

Expiration: 12months at room temperature. It will be better to finish the products within 6months after open.

6 使用注意事项 ATTENTIONS

将A和B两组分混合时,配比不准确将会影响硫化过程和制品性能,因此一定要准确控 制比例。

Strictly control percentage of A and B when mixing, for vulcanization and properties will be affected under wrong ratio.

硫化时间决定于硫化温度及制品厚度, 具体硫化时间要根据实际情况调整

Time of vulcanization depends on manufacturing and thickness of products. It should be adjusted according to different situation.

如果胶料接触某些如含氮、磷、硫、锡等化合物的物质,则会抑制硫化反应,严重将导

地址 (Address): 中国广东省清远市高新技术产业开发区井岭路36号

No.36, Jingling Road, Qingyuan High-tech Zone, Qingyuan Guangdong China.

电话 (Tel): (+86) 0763-3608674 传真 (Fax): (+86) 0763-3608675

网址 (Website): www.wynca.com ●邮编(Postcode):511500



品说明书

TECHNICAL DATA SHEET

致产品不硫化,应极力避免和此类物质 接触。

Avoid mix products with nitrogen, phosphorus, sulfur and tin, etc. These materials may affect or stop vulcanization.

7 使用工艺 USE OF TECHNOLOGY

本产品是A和B双组分包装提供的,按10:1比例混合使用。建议用静态混合设备混合,可 以隔绝空气。如果混合过程中带入气泡,必须彻底排气。建议硫化温度在120℃-150℃,最 终以实际产品设计需求为准。

This product is composed by A & B packages. Suggest using in percentage 10:1. Please mix A & B without air in staticmixing equipment. Make sure releasing air if there are bubbles when mixing. It is suggested that the curing temperature should be between 120°c and 150°c, and the actual product design requirements should prevail.

TYPICAL PROPERTY DATA 8 典型数据

Test Item 检测指标	Unit 单位	Test Conditions 测试条件	Test Method 测试方法	Data 数据		
				A component A组分	B component B组分	
Appearance 胶料外观				colourless-transparent 无色透明	colourless-transparent 无色透明	
Dynamic Viscosity 动力粘度	10^4mPa⋅s	6#, 20rpm	DIN 53019-1	10.0		
Density 密度	g/cm ³	105℃×15min	ISO 2781	1.090		
Hardness 硬度	НА	105℃×15min	ISO 48-4	41.23/19		MAuca
Tensile Strength 拉伸强度	MPa	105℃×15min	JIS K 6251 Type	7.5		143
Elongation 伸长率	%	105℃×15min	JIS K 6251 Type	480		
Tensile Set 拉伸永变	%	105℃×15min	JIS K 6251 Type	2.0		
Tear Strength 撕裂强度	N/mm	105℃×15min	ISO 34-1 Die B	uncaillié	5.0 mca # 5	

上述表中所列物性数据仅供参考,若需要货物的检验报告,请向销售办事处索取。 The data is just for reference, For performance data and safety information of specified products, please contact the Wynca Tinyo Silicone CO., LTD.

地址 (Address): 中国广东省清远市高新技术产业开发区井岭路36号

No.36, Jingling Road, Qingyuan High-tech Zone, Qingyuan Guangdong China.

电话 (Tel): (+86) 0763-3608674 传真 (Fax): (+86) 0763-3608675

网址 (Website): www.wynca.com 邮编(Postcode): 511500



品说明书

9 工业使用说明 FOR INDUSTRIAL USE

使用者有义务对将使用新安天玉有机硅有限公司产品的适用范围以及用途进行了解;请 勿将新安天玉有机硅有限公司产品用作移植或注入人体用途。

The user has the obligation to understand the scope of application and use of the products of Wynca Tinyo Silicone CO.,LTD. Our products can not be implanted or injected into the human body.

我们随货的检测报告仅是新安天玉有机硅有限公司实验室依据新安天玉有机硅有限公司 的硫化条件和检测方法测试所得,它不能够作为新安天玉有机硅有限公司液体胶产品标 准使用,不能作为客户接受新安天玉有机硅有限公司产品的验收依据。

Our inspection report is only obtained by the laboratory of Wynca Tinyo Silicone Co., Ltd. according to the vulcanization conditions and detection methods of Wynca Tinyo Silicone Co., Ltd, It can not be used as the standard of Wynca Tinyo Silicone Co., Ltd. and can not be used as the acceptance basis for customers to accept the products of Wynca Tinyo Silicone Co., Ltd.

由于检测生产条件不同,我们不能保证我们双方能得到同样的测试结果,建议使用者 在自己的检测条件下测试所得的数据作为使用性能的参考。

Due to the different testing and production conditions, we cannot guarantee that we can get the same test results. We suggest users to use the test data obtained under their own testing conditions as a reference for performance.

以上任何性能数据及使用建议,只是对新安天玉有机硅有限公司产品使用性能的一个使 用参考,而不是新安天玉有机硅有限公司产品在特定应用下的有效性或通用性担保。

Any of the above performance data and usage suggestions are only a reference for the performance of the products of Wynca Tinyo Silicones Co., Ltd., and are not a guarantee of the effectiveness or versatility of the products of Wynca Tinyo Silicones Co., Ltd. in specific applications.

我们保留变更产品参数的权利,若有任何改动,不另行通知。

We reserve the right to change the product parameters without prior notice.

发布日期(Issued): 2024-10-22

地址 (Address): 中国广东省清远市高新技术产业开发区井岭路36号

No.36, Jingling Road, Qingyuan High-tech Zone, Qingyuan Guangdong China.

电话 (Tel): (+86) 0763-3608674 传真 (Fax): (+86) 0763-3608675 网址 (Website): www.wynca.com ●邮编(Postcode):511500